

Short Communication

## $\beta$ -Ga<sub>2</sub>O<sub>3</sub> Particles Formed of a Complex Organic by Electrolysis

F.G. Nieto-Caballero<sup>1,\*</sup>, G. García-Salgado<sup>2</sup>, T. Díaz-Becerril<sup>2</sup>, E. Rosendo-Andrés<sup>2</sup>,  
H. Juárez-Santiesteban<sup>2</sup>, M. Gracia-Jiménez<sup>3</sup>, A. Tovar-Corona<sup>1</sup>, U. Peña-Rosas<sup>1</sup>, R. Peña-Sierra<sup>4</sup>

<sup>1</sup> Facultad de Ciencias Químicas. Benemérita Universidad Autónoma de Puebla. 14 Sur y Avenida San Claudio. Ciudad Universitaria. Puebla. Pue.

<sup>2</sup> Centro de investigaciones en Dispositivos Semiconductores (CIDS-ICUAP). Benemérita Universidad Autónoma de Puebla. 14 Sur y Avenida San Claudio. Ciudad Universitaria. Puebla. Pue.

<sup>3</sup> Instituto de Física (IFUAP), Benemérita Universidad Autónoma de Puebla. 18 Sur y Avenida San Claudio. Ciudad Universitaria. Puebla. Pue.

<sup>4</sup> Sección de Electrónica y Estado Sólido (SEES-CINVESTAV), México D.F.

\*E-mail: [ruscaballero@yahoo.com.mx](mailto:ruscaballero@yahoo.com.mx)

Received: 26 May 2015 / Accepted: 2 September 2015 / Published: 30 September 2015

---

$\beta$ -Gallium oxide particles were obtained by electrolysis from a complex of gallium-carbohydrazide, using as electrolyte ethanol and subsequently annealing at 900 °C in N<sub>2</sub>, O<sub>2</sub>, or O<sub>3</sub> atmosphere during 1 hr. The particles were deposited on c-Si wafers for 30 minutes with a current density of 15 mA cm<sup>-2</sup>. Heat treatment breaks down the complex and lead to the formation of Ga<sub>2</sub>O<sub>3</sub>, but the amount of oxide formed is modified according to the atmosphere of treatment. It is observed the semiconductor material formation in presence of oxygen, and to a lesser extent in nitrogen or ozone atmospheres. The influence of annealing atmosphere is reflected in the surface morphology and the optical properties of Ga<sub>2</sub>O<sub>3</sub> particles, which were investigated by X-ray diffraction (XRD), energy dispersive X-ray (EDS), micro-Raman and UV-Vis spectroscopy.

---

**Keywords:** gallium oxide, electrolysis, x-ray diffraction, complex.

### 1. INTRODUCTION

Monoclinic gallium oxide ( $\beta$ -Ga<sub>2</sub>O<sub>3</sub>) is a wide band gap semiconductor, which has wide applications as optical windows, semiconducting laser, high-temperature stable gas sensor, dielectric thin film. Gallium oxide occurs in various structures like  $\alpha$ ,  $\beta$ ,  $\gamma$ ,  $\sigma$ ,  $\epsilon$  types, and the monoclinic  $\beta$ -Ga<sub>2</sub>O<sub>3</sub> is considered to be the equilibrium phase [1-3]. The  $\beta$ -Ga<sub>2</sub>O<sub>3</sub> possesses excellent optical properties, it is highly transparent in visible and near UV range of wavelengths and enhancement of

transmittance could be obtained by increase of oxide layer deposition temperature or appropriate annealing of crystals [4-7].

One of the parameters influencing the band gap is temperature annealing of deposited layer [8]. Recently, several groups have reported the growth of  $\beta$ -Ga<sub>2</sub>O<sub>3</sub> by several methods as molecular beam epitaxy (MBE) [9,10], electron beam evaporation [11], spray pyrolysis, rf-magnetron sputtering, low-pressure flame, pulsed laser ablation [12]. There are other methods to obtain gallium oxide, the main ways are: chemical oxidation, thermal oxidation, anodic oxidation, plasma oxidation, etc. These oxidation processes use GaAs and GaN with sources of O<sub>2</sub>, N<sub>2</sub>O or CO<sub>2</sub>, for the oxide formation [8]. The electro-crystallization from aqueous solution is a powerful technique for growing high-quality semiconducting oxides, and offers epitaxial growth as well as low-cost, low-temperature, and scalable process. Recently several binary oxides, such as ZnO, CeO<sub>2</sub>, TiO<sub>2</sub>, and Ag<sub>2</sub>O<sub>2</sub>, have been prepared electrochemically [13]. It has been reported that the oxidation of semiconductors using electrochemical anodic process is similar to typical process of oxide layer manufacturing in electrolyte. Anodic process is more efficient if in the semiconductor material holes occur (p type electrical conduction). For n type it is necessary to generate holes in order to get an oxidation; the best is using appropriate photon energy. After anodic process of GaAs there are a mixture of arsenic and gallium oxides, these layers of oxide should be annealed at high temperature (more than 450 °C), because of that high temperature those layers dissociate arsenic oxide and gallium oxide and become crystalline [8]. The anodic oxidation of n-type GaN under laboratory illumination at a constant current density of 5 mA·cm<sup>-2</sup> and sodium tungstate electrolyte at 298 K was made by Pakes, and obtained an oxide non-uniform and texture with pore-like features [14]. On the other hand, has been reported the combustion synthesis for the production of InGaO powders using hydrazine and the combustion reaction occurred by heating the precursors between 150 and 200°C onto closed vessel filled with an inert gas (Ar) [15]. Recently Ghazali report a synthesis of  $\beta$ -Ga<sub>2</sub>O<sub>3</sub> nanostructures over c-Si by electrochemical deposition using a mixture of Ga<sub>2</sub>O<sub>3</sub>, HCl, NH<sub>4</sub>OH and H<sub>2</sub>O [16], and K. Girija reports the preparation of  $\beta$ -Ga<sub>2</sub>O<sub>3</sub> nanorods through reflux condensation process, with reflux at 90 °C of 12 hours, and to get a calcinations at 900 °C for 3 hours, indicating that there is a phase transition from  $\alpha$ -Ga<sub>2</sub>O<sub>3</sub> to  $\beta$ -Ga<sub>2</sub>O<sub>3</sub> above 600 °C [17]. This document describes the synthesis of gallium complex by the electrolysis technique at room temperature, and we have demonstrated the easier crystallization of this complex to  $\beta$ -Ga<sub>2</sub>O<sub>3</sub> particles with annealing at 900 °C in O<sub>2</sub> by an hour. The particles obtained were characterized by XRD, EDS, UV-Vis and micro-Raman spectroscopy.


## 2. EXPERIMENTAL

The particles were prepared by electrolysis with solutions 0.1 M of gallium nitrate hydrate (Ga(NO<sub>3</sub>)<sub>3</sub>, Aldrich 99.9 %) and 0.1 M of carbohydrazide (CH<sub>6</sub>N<sub>4</sub>O, Fluka 98 %) reagent grade chemicals and deionized water. As a substrate and anode, a boron doped p-type (100) c-Si wafer with 0.01-0.02 ohm-cm resistivity was used; the substrates were cleaned with xylene, acetone and methanol using an ultrasonic bath. The electrolytic process was carried out using as electrolyte 5 ml of ethanol (99.98%) and 5 ml of a solution prepared of gallium nitrate-carbohydrazide. A power source Keithley

model 2400 was used to deliver the controlled current, working with a constant current density (J) of 15 mA over 1.0 cm<sup>2</sup> of exposed area of the Si substrate for 30 min. After the electrolysis, the deposited material was dried at room temperature. The samples obtained with the same growth conditions were annealed in atmosphere of ozone, oxygen or nitrogen at 900 °C by an hour, in order to observe the effect in the structural and optical properties. The samples were characterized by XRD; with a diffractometer Bruker, AXS-D8 Discover (Cu K $\alpha$  radiation). The Carl Zeiss Auriga 60, coupled with a Bruker Quantex instrument was using to analysis EDS. The ultraviolet-visible (UV-Vis) spectroscopy was made by an instrument Evolution 600 with a diffuse reflectance accessory and the studies of Micro-Raman were made using a spectrometer Jobin-Yvon (Horiba) with the 632 nm line of a He-Ne laser.

### 3. RESULT AND DISCUSSION

Figure 1 shows the XRD pattern of four samples; as synthesized and annealed in O<sub>3</sub>, O<sub>2</sub> or N<sub>2</sub>. The patterns corresponding to annealing samples show all the detectable diffraction peaks identified to  $\beta$ -Ga<sub>2</sub>O<sub>3</sub> (according PDF card no. 01-076-0573) phase with lattice constants of a=1.223, b=0.304, c=0.580 nm and  $\alpha=90^\circ$ ,  $\beta=103.7^\circ$ ,  $\gamma=90^\circ$ .





**Figure 1.** XRD patterns of samples obtained as synthesized (a), and with annealed at 900 °C in b) O<sub>3</sub>, c) O<sub>2</sub> and d) N<sub>2</sub>.

In the sample as synthesized (S7) (Fig. 1, a) there is a peak of diffraction at  $2\theta = 25^\circ$ , which corresponds to the organic impurities deposited. The sample with annealing in ozone (S6) (Fig. 1, b) shows again the peak corresponding to the impurities deposited, in addition lines associated with the  $\beta$ -

Ga<sub>2</sub>O<sub>3</sub> phase are observed. The samples annealed with nitrogen and oxygen (S4 and S5 respectively) only present peaks associated to β-Ga<sub>2</sub>O<sub>3</sub>. An important difference between XRD patterns is observed; the sample annealed in oxygen (S5) shows a major intensity (an order of magnitude higher), therefore a better crystalline quality. The dominant peak in the XRD pattern of sample with annealing in oxygen is β-Ga<sub>2</sub>O<sub>3</sub> (002) with 2θ = 31.7 °corresponding to base-centered monoclinic structure.

The result of the analysis of EDS for the samples as synthesized and annealed in O<sub>2</sub> is shown in the Figure 2. In the pictures are observed two aspects, the first is the modification of the surface after the heat treatment applied and the second is the distribution of the atomic species contained in the material.





**Figure 2.** Pictures and EDS spectrum of samples as synthesized (a, c and e) and with annealed at 900 °C in O<sub>2</sub> (b, d and f)


In Figure 2 (a) is observed in the morphology of the sample as synthesized (S7) a texture in the form of plates, and Figure 2 (c) shows the distribution of atomic species that are present in the material, which are gallium, oxygen, nitrogen and carbon. There are three sites with a high concentration of gallium atoms in isolated regions, however this is an anomalous behavior, the characteristic distribution of the atomic species is homogeneous. The image of the sample with heat treatment in oxygen (S5) (Figure 2 (b-d)) shows a rough texture and the distribution of gallium and oxygen atoms is uniform. In the spectrum (Figure 2 (f)) the signal corresponding to the nitrogen is removed and the amount of carbon is significantly reduced, this indicates that these elements were desorbed with heat treatment.

The growth of materials involves the process of precipitation, followed by nucleation and particle growth stage, during the growth stages of β-Ga<sub>2</sub>O<sub>3</sub>, the process of hydrolysis and condensation takes place [6]. In the electrolysis process it is carried out the precipitation of metal cations, carbohidrazyde and ethanol to obtain the complex of gallium, and it is proposed the following reaction mechanism: the gallium nitrate in water dissociates into gallium ions (Ga<sup>3+</sup>), and the water provides hydroxyl ions (E1, E2).



The ethanol and carbohidrazyde in the presence of H<sup>+</sup> generated ions (E3-E4).






The ion N<sub>4</sub>H<sub>6</sub>C-OH<sup>+</sup> is unstable and is considered that the positive charge moves to the atom carbon (E4).

Also it is known that carbohydrazide is an azotic ligand with lone electron pairs, and may coordinate with some metal ions as multidentate forming chelates. Carbohydrazide runs as a tridentate binder that captures metal by the oxygen and nitrogen of NH<sub>2</sub> groups, as shown in Figure 3 [18].



**Figure 3.** Metal-carbohydrazide complexes [18].

When is applied the current, the positive ions are directed towards the silicon surface and is formed the complex (carbohydrazide-gallium-ethanol).




**Figure 4.** The complex carbohydrazide-gallium-ethanol proposed. Image taken and modified from A. Kagkelari [19].

It is reported that the geometry of the complexes is planar [19]. With applied thermal treatment is carrying out the hydroxylation of metallic ion and subsequent dehydration, forming products in phase gas, and on the surface β-Ga<sub>2</sub>O<sub>3</sub> according to the following reaction (E5).



The absorption spectra (Figure 5) clearly exhibit the changes in the absorbance edges corresponding to the energy band gap of  $\beta$ -Ga<sub>2</sub>O<sub>3</sub>. This semiconductor is a direct-band gap material and the optical band gap can be determined from absorption spectra. It obeys the relation  $\alpha h\nu = A(h\nu - E_g)^{1/2}$ , where A is a constant, E<sub>g</sub> is the optical band gap, and  $\alpha$  is the absorption coefficient. By extrapolating a plot of  $(\alpha h\nu)^2$  versus  $h\nu$  to  $\alpha=0$ , the optical band gap can be obtained. The as-grown sample (S7) shows gradual absorption at 250 nm, indicating that the sample is amorphous, also presents a change in 300 nm (\*), which is due to the gallium complex deposited, it is known that the absorption characteristic of group -C=O ( $\pi^* \leftarrow n$ ) takes place in 270-290 nm and corresponds to carbonyl [20]. The annealing samples in O<sub>3</sub>, O<sub>2</sub> and N<sub>2</sub>, shows a similar response, but the change in the absorption shifts towards lower wavelength, the signal in 300 nm disappears, the crystallization of the deposited particles were sensitive to the annealing temperature and atmosphere. The optical band gap of the as-grown, O<sub>3</sub>, O<sub>2</sub> or N<sub>2</sub> (S6, S5 and S4 respectively) annealed samples are shown in the table 1, where the values in wavelength are approaching the value reported in the band gap of gallium oxide [11].




**Figure 5.** UV-Vis spectra of samples obtained as synthesized and with annealed at 900 °C in O<sub>3</sub>, O<sub>2</sub> or N<sub>2</sub>.

**Table 1.** Band gap values obtained

Sample	$\lambda$ (nm)	Energy (eV)
As synthesized (S7)	250	4.93 eV
Annealed at 900 °C in O <sub>3</sub> (S6)	280	4.41 eV
Annealed at 900 °C in O <sub>2</sub> (S5)	277	4.48 eV
Annealed at 900 °C in N <sub>2</sub> (S4)	277	4.48 eV

The Raman spectra obtained of the samples are shown in Figure 6. All spectra show a signal at  $304\text{ cm}^{-1}$  which corresponds to the substrate. The Raman lines active for  $\beta\text{-Ga}_2\text{O}_3$  are at  $104.7, 163.5, 202.3, 315.8, 339.7, 420.2, 459.4, 607.1, 656.1$  and  $757.7\text{ cm}^{-1}$  corresponding to the modes of optical vibration [21]. In the samples with thermal annealing can be seen a low intensity signal in  $203\text{ cm}^{-1}$ , this value is so close to theoretical value reported characteristics of the monoclinic  $\text{Ga}_2\text{O}_3$ , the intensity is slightly higher in the sample with annealing in oxygen.



**Figure 6.** Micro-Raman spectra of samples obtained as synthesized and with annealed at  $900\text{ }^\circ\text{C}$  in  $\text{O}_3$ ,  $\text{O}_2$  or  $\text{N}_2$ .

#### 4. SUMMARY

It was synthesized and investigated gallium complex on silicon substrates by electrolysis with gallium nitrate as precursor. The particles obtained were complex amorphous and the annealing to  $900\text{ }^\circ\text{C}$  with oxygen enhances their crystallization. The material obtained was  $\beta\text{-Ga}_2\text{O}_3$  with crystalline monoclinic phase and high purity, evidenced from the XRD and Raman analysis. It is proposed that during the process of electrolysis a carbonyl-gallium-ethanol organic complex was formed, according to the analysis of EDS and UV-Vis spectroscopy. The temperature and annealing time used in this growth process were lower with respect to the required in another technique.

#### ACKNOWLEDGEMENTS

The authors wish to thank the VIEP-BUAP for the support given to the development of this project.

#### References

1. F. A. Cotton, G. Wilkinson. Química Inorgánica Avanzada. Editores Noriega Limusa (1995).

2. Takeyuki Sekimoto, Masahiro Deguchi, Satoshi Yotsuhashi, Yuka Yamada, Takekazu Masui, Akito Kuramata, Shigenobu Yamakoshi, *Electrochemistry Communications*, 43 (2014) 95-97.
3. Xiaohe Liu, Guanzhou Qiu, Yan Zhao Ning Zhang, Ran Yi, *Journal of Alloys and Compounds* 439 (2007) 275-278.
4. Yoshinori Tokida, Sadao Adachi, *Journal of Solid State Science and Technology*, 3 (6) (2014) 100-103.
5. Bong Kyun Kang, Sung Ryul Mang, Da Hyeon Go, Dae Ho Yoon, *Materials Letters*, 111 (2013) 67-70.
6. K. Girija, S. Thirumalairajan, Astam K. Patra, D. Mangalaraj, N. Ponpandian C. Viswanathan, *Current Applied Physics*, 13 (2013) 652-658.
7. Manickavachagam Muruganandham, Rominder Suri, Mahmoud S.M. Abdel Wahed, Mika Sillanpää, Bashir Ahmmad, Gang-Juan Lee, Jerry J. Wu, *Materials Letters*, 111 (2013) 137-139.
8. Semiconductor Technologies. Cap.6. Ryszard Korbutowicz, Joana Prazmowska. Wroclaw University of Technology Poland. ([www.intechopen.com](http://www.intechopen.com)).
9. Kohei Sasaki, Masataka Higashiwaki, Akito Kuramata Takekazu Masui, *Journal of Crystal Growth*, 378 (2013) 591-595.
10. Y.C. Chang, Y.J. Lee, Y.N. Chiu, T.D. Lin, S.Y. Wu, H.C. Chiu, J. Kwo, Y.H. Wang, M. Hong, *Journal of Crystal Growth*, (2007) 301-302.
11. Yi Cheng, Hongwei Liang, Yang Liu, Xiaochuan Xia, Rensheng Shen, Shiwei Song, Yunfeng Wu, Guotong Du, *Materials Science in Semiconductor Processing*, 16 (2013) 1303-1307.
12. Tingting Zhang, Jing Lin, Xinghua Zhang, Yang Huang, Xuewen Xu, Yanming Xue, Jin Zou, Chengchun Tang, *Journal of Luminescence*, 140 (2013) 30-37.
13. Tsutomu Shinagawa, Yuya Ida, Kotaro Mizuno, Seiji Watase, Mitsuru Watanabe, Minoru Inaba, Akimasa Tasaka, Masanobu Izaki, *Crystal Growth E Design*, 13 (2013) 52-58.
14. Pakes, A., Skeldon P., G. E. Thompson, J. W. Fraser, S. Moisa, G. I. Sproule, M. J. Graham, S. B. Newcomb. *Journal of Materials Science*, Vol.38, No. 2 (2003) 343-349.
15. R. García, G.A. Hirata, J. McKittrick, *Journal Materials Research*, 16 (4) (2001) 1059-1065.
16. Norizzawati Mohd Ghazali, Mohamad Rusop Mahmood, Kanji Yasui, Abdul Manaf Hashim, *Nanoscale Research Letters*, 9 120 (2014) 1-7.
17. K. Girija, S. Thirumalairajan, Astam K. Patra, D. Mangalaraj, N. Ponpandian, C. Viswanathan, *Current Applied Physics*, 15 (2013) 652-658.
18. Mohammed Gaber, Shar S. Al Shihry. *Scientific Journal of King Faisal University*, Vol.5 No. (2) 1425 (2004) 181-194.
19. Kagkelari V., Bekiari E., Stathatos, G. S. Papaefstathiou, C. P. Raptopoulou, T. F. Zafirooulos, P. Lianos, *Journal of Luminescence*, 129 (2009) 578-583.
20. R.A. Day, A. L. Underwood. *Química Analítica Cuantitativa*. 5ª. Edición, Prentice Hall (1989).
21. Bo Liu, Mu Gu, Xiaolin Liu, *Applied Physics Letters*, 91 (2007) 172102.